

## Teknos AQUAPRIMER 2907-42

AU\_DW02470

### Description

AQUA PRIMER 2907 – 42 is an opaque spray applied combi-primer designed to help protect wood surfaces against mould, fungus and blue stain. Recommended for use on Accoya and suitable for most other timber used in exterior applications.

### Features

Designed to help protect wood surfaces against mould, fungus and blue stain.

### Benefits

Recommended for use on Accoya and suitable for most other timber used in exterior applications.





### Uses

AQUA PRIMER 2907-42 is an aqueous industrial opaque combi-primer for wood designated for exterior use  
The product protects the wood surface and the treated area against wood discolouring fungi  
AQUA PRIMER 2907-42 minimises yellowing at knots / heartwood.

### Precautions And Limitations

Treated parts must always be protected with a topcoat treatment before they are exposed to the influence of the weather

### Typical Properties

Colour	White	V.O.C. Level	17																				
Meets GBCA VOC Requirement?	Yes. Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.																						
Clean Up	 Water																						
Application Method	 Air Spray  Airless Spray  Electrostatic Spray																						
Application Conditions	<table> <thead> <tr> <th></th><th>Min</th><th>Max</th><th>Recommended</th></tr> </thead> <tbody> <tr> <td>Wet Film Per Coat (microns)</td><td>169</td><td>179</td><td></td></tr> <tr> <td>Dry Film Per Coat (microns)</td><td></td><td></td><td></td></tr> <tr> <td>Recoat Time (min)</td><td></td><td></td><td>120 -180</td></tr> <tr> <td>Theoretical Spread Rate (m<sup>2</sup>/L)</td><td></td><td></td><td></td></tr> </tbody> </table>				Min	Max	Recommended	Wet Film Per Coat (microns)	169	179		Dry Film Per Coat (microns)				Recoat Time (min)			120 -180	Theoretical Spread Rate (m <sup>2</sup> /L)			
	Min	Max	Recommended																				
Wet Film Per Coat (microns)	169	179																					
Dry Film Per Coat (microns)																							
Recoat Time (min)			120 -180																				
Theoretical Spread Rate (m <sup>2</sup> /L)																							
Typical Properties Notes	Drying times: Determined at 20 °C and 50 % relative humidity: Dry to handle: 2-3 hours Dry to sand / recoat: 3-4 hours The drying time can be reduced using special drying systems to force drying. The drying times are approximate and may vary according to wood quality, temperatures, humidity and ventilation.																						

### Application Guide

Surface Preparation	<ul style="list-style-type: none"> <li>The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %.</li> </ul>
Application Procedure And Equipment	<ul style="list-style-type: none"> <li>Spraying conditions: Nozzle Pressure Air support Airless flat 0.28 mm 100-110 bar Aircoat flat 0.28 mm 80-100 bar 1.0-1.5 bar</li> </ul>

### Health And Safety

In the case of emergency, please call 1800 033 111

**Disclaimer**

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427